



**CP02-N0003**

**ASA**

Good Flow, Processability, and Impact  
 \*\*Available in Natural & Colors

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Melt Flow (220°C / 10.0 kg)	ASTM D1238	14.0	g/10 min
Melt Flow (230°C / 3.8 kg)	ASTM D1238	4.0	g/10 min
Specific Gravity	ASTM D792	1.07	
Mold Shrink, Linear Flow (.125 in)	ASTM D955	0.006	in/in

**Impact**

Notched Izod Impact (.125 in)			
73°F	ASTM D256	3.3	ft-lbs/in
-40°F	ASTM D256	0.9	ft-lbs/in

**Mechanical**

Tensile Modulus (.2 in/min)	ASTM D638	360,000	psi
Tensile Strength @ Yield (2 in/min)	ASTM D638	7,500	psi
Tensile Elongation @ Break (2 in/min)	ASTM D638	15.0	%
Flexural Strength @ Yield	ASTM D790	11,400	psi
Flexural Modulus	ASTM D790	365,000	psi

**Thermal**

Deflection Temperature Under Load			
.125 in, 66 psi, Unannealed	ASTM D648	202	°F
.125 in, 264 psi, Unannealed	ASTM D648	181	°F

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

**Recommended Processing Parameters**

Drying Temperature	175°F
Drying Time	3-4 hrs.
Suggested Maximum Moisture Content	0.1%
Rear Temperature	440 - 500 °F
Middle Temperature	450 - 510 °F
Front Temperature	460 - 520 °F
Nozzle Temperature	460 - 520 °F
Processing (Melt) Temperature	460 - 520 °F
Mold Temperature	100 - 160 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.