



CP07-N0040

Polyamide 66

35% Hydrolysis Resistant Glass Fiber Reinforcement, Heat Stabilized

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Specific Gravity	ASTM D792	1.41	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.004	in/in

Impact

Notched Izod Impact (.125 in) 73°F	ASTM D256	2.2	ft-lbs/in
---------------------------------------	-----------	-----	-----------

Mechanical

Tensile Strength @ Break	ASTM D638	30,000	psi
Tensile Elongation @ Break	ASTM D638	3.2	%
Flexural Strength	ASTM D790	43,500	psi
Flexural Modulus	ASTM D790	1,375,000	psi

Thermal

Deflection Temperature Under Load 264 psi	ASTM D648	491	°F
--	-----------	-----	----

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

Recommended Processing Parameters

Drying Temperature	180°F
Drying Time	3.0 - 4.0 Hours
Suggested Maximum Moisture Content	0.15%
Rear Temperature	480 - 550 °F
Middle Temperature	480 - 550 °F
Front Temperature	480 - 550 °F
Nozzle Temperature	480 - 550 °F
Processing (Melt) Temperature	480 - 550 °F
Mold Temperature	160 - 240 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.