



CP10-N0003
Polyether Imide

10% Glass Fiber Reinforcement

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Melt Flow @ 337°C / 6.6 kg	ASTM D1238	8.0	g/10 min
Specific Gravity	ASTM D792	1.34	
Mold Shrink, Linear Flow (.125 in)	ASTM D955	0.006	in/in

Impact

Notched Izod Impact (.125 in) 73°F	ASTM D256	0.9	ft-lbs/in
---------------------------------------	-----------	-----	-----------

Mechanical

Tensile Strength @ Yield	ASTM D638	16,000	psi
Tensile Elongation @ Break	ASTM D638	5.5	%
Flexural Strength @ Break	ASTM D790	28,500	psi
Flexural Modulus	ASTM D790	725,000	psi

Thermal

Deflection Temperature Under Load			
.250 in, 66 psi	ASTM D648	408	°F
.250 in, 264 psi	ASTM D648	406	°F

Flammability

Flame Rating (.0625")	V-0
Flame Rating (.125")	5VA

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

Recommended Processing Parameters

Drying Temperature	300°F
Drying Time	4.0 - 6.0 Hours
Suggested Maximum Moisture Content	0.02%
Rear Temperature	620 - 740 °F
Middle Temperature	630 - 740 °F
Front Temperature	640 - 740 °F
Nozzle Temperature	640 - 740 °F
Processing (Melt) Temperature	650 - 740 °F
Mold Temperature	280 - 330 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.