



CP56-N0002

PPE/PS Alloy

20% Glass Fiber Reinforcement

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Specific Gravity	ASTM D792	1.20	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.004	in/in

Impact

Notched Izod Impact (.125 in) 73°F	ASTM D256	1.8	ft-lbs/in
---------------------------------------	-----------	-----	-----------

Mechanical

Tensile Strength @ Break	ASTM D638	12,000	psi
Tensile Elongation @ Break	ASTM D638	2.5	%
Flexural Strength	ASTM D790	19,700	psi
Flexural Modulus	ASTM D790	840,000	psi

Thermal

Deflection Temperature Under Load .250 in, 66 psi	ASTM D648	285	°F
.250 in, 264 psi	ASTM D648	275	°F

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

Recommended Processing Parameters

Drying Temperature	240°F
Drying Time	3.0 - 4.0 Hours
Suggested Maximum Moisture Content	0.02%
Rear Temperature	500 - 590 °F
Middle Temperature	520 - 600 °F
Front Temperature	540 - 610 °F
Nozzle Temperature	560 - 610 °F
Processing (Melt) Temperature	560 - 610 °F
Mold Temperature	180 - 240 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.