



**CP56-N0028**

**PPE/PS Alloy**

10% Glass Fiber Reinforcement

5401 N Hwy 41 / Suite 1000 Evansville, IN 47711 • Phone: 812.426.1350 • FAX: 888.855.3671 • www.cpptech.com

Physical	Method	Typical Value	Units
Specific Gravity	ASTM D792	1.13	
Mold Shrink, Flow: 0.125 in	ASTM D955	0.005	in/in

**Impact**

Notched Izod Impact (.125 in) 73°F	ASTM D256	2.2	ft-lbs/in
---------------------------------------	-----------	-----	-----------

**Mechanical**

Tensile Strength @ Break	ASTM D638	8,200	psi
Tensile Elongation @ Break	ASTM D638	2.8	%
Flexural Strength	ASTM D790	14,000	psi
Flexural Modulus	ASTM D790	550,000	psi

**Thermal**

Deflection Temperature Under Load .250 in, 66 psi	ASTM D648	262	°F
.250 in, 264 psi	ASTM D648	252	°F

Information provided is based on typical values from reliable procedures. Values are based on natural or black materials unless otherwise noted. No guarantees or warranties of any kind are expressed or implied. Users are responsible for determining the suitability of the product for their intended application.

**Recommended Processing Parameters**

Drying Temperature	225°F
Drying Time	3.0 - 4.0 Hours
Suggested Maximum Moisture Content	0.02%
Rear Temperature	490 - 570 °F
Middle Temperature	510 - 580 °F
Front Temperature	530 - 590 °F
Nozzle Temperature	550 - 590 °F
Processing (Melt) Temperature	550 - 590 °F
Mold Temperature	170 - 220 °F

CPPT recommended processing parameters are meant to serve as guidelines only and are not intended to be used for specification purposes. Conditions should be adjusted to optimize material performance with the equipment part design and tooling.